

EXTENDING THE LIFE OF EXTRACTED NATURAL RESOURCES

## Flexisurf Chemical Resistance Data

Acid Rain	Ethyl Alcohol	Phthalic Acid
Acrylic Paint	Ferric Chloride	Polyethylene
Aluminum Chloride	Fertilizer Solution	Polypropylene
Ammonium Hydroxide	Fiberglass Mat	Potassium Chloride
Ammonium Chloride	Formaldehyde	Pork Fat
Ammonium Nitrate	Fruit Juice	Rain
Ammonium Sulfate	Furnace Residue	Salt
Amyl Acetate	Gasoline	Salt Water
Aniline	Glyoxal	Sea Water
Battery Acid	Hydrogen Peroxide	Sewer Sludge
Beef Fat	Ice Cream	Soda Pop
Beer	Incinerator Ashes	Sodium Hydroxide
Benzoic Acid	Jet Fuel	Sodium Hypochlorite
Bird Droppings	Kerosene	Soldering Acid
Bleach	Lacquer Spray Paint	Soldering Flux
Borax	Lanolin	Soybean Oil
Boric Acid	Lard	Stones
Brick & Masonry Cleaner	Latex Paint	Succinic Acid
Butyric Acid	Lactic Acid	Tea
Butter	Linseed Oil	Tannic Acid
Butyl Acetate	Malic Acid	Tree Sap
Calcium Chloride	Methyl Alcohol	Triacetin
Calcium Hydroxide	Milk	Trichloroacetic Acid
Calcium Hypochlorite	Mineral Oil	Trichloroethylene
Chromic Acid	Mineral Spirits	Triethanolamine
Coconut Oil	Mud	Triethylene Glycol
Coffee	Muriatic Acid	Urea
Cooking Grease	Naphtha	Urine
Copper Sulfate	Naphthalene	Vegetable Oil
Corn Oil	Oleic Acid	Whiskey
Cotton Seed Oil	Olive Oil	Wine
Cutting Oil	Oxalic Acid	Yeast
Detergent Solution	Palm Oil	Yogurt
Diatomaceous Earth	Paper	Zinc Chloride
Diglycolic Acid	Perchloroethylene	Zinc Nitrate
Diethyl Phthalate	Phosphoric Acid	

The information accumulated herein is believed to be accurate but is not warranted to be whether originating with the company or not. Recipients are advised to confirm in advance of need that the information is current, applicable and suitable to their circumstances. Since the use of this material is beyond our control, no guarantees are expressed or implied and Yemm & Hart Ltd assumes no liability.